

Sealants / Polyurethane Sealants

PU 970

Polyurethane Low Modulus Sealant (LM)

DESCRIPTION

Polyurethane based, single component, **low modulus (LM)** sealant which is an ideal product for **static** and **dynamic** expansion joints of construction elements.

APPLICATION AREAS

- Indoor and outdoor,
- Horizontal and vertical dilatation joints,
- Roof and terrace dilatations and joints of parapet corners,
- Intersection details of prefabricated elements,
- Between precast wall panels,
- As a sealant in joints of PVC, wood, metal, aluminum and plastic joinery.

TECHNICAL PROPERTIES

Appearance	High viscosity polyurethane sealant
Color	Pls.see color chart
Density	1.15 ± 0.05 g/cm ³ (DIN 53479)
Surface Dry Time	90 ± 30 minutes
Application Temperature	Between +5°C and +35°C
Curing Rate	2 mm / 24 hours
Elongation at Break	> 1000% (14 days) (DIN 53504)
Hardness (Shore A)	25 ± 5 (DIN 53505)
Tensile Strength	> 1.5 N/mm ² (DIN 53504)
100% Modulus	> 0.40 N/mm ² (DIN 53504)
Volume Change	~ 5%
Sagging	< 2 mm (DIN EN ISO 7390)
Service Temperature	Between -30°C and +80°C

ADVANTAGES

- Easy to apply and its surface can be smoothed.
- Has high stretching properties and turns its original form.
- Has perfect and permanent elasticity and adhesion strength.
- Tolerates even the small movements of the building thanks to its low modulus.
- Hardens with atmospheric moisture.
- Can be overpainted.
- Watertight seal after curing.
- Resistant to aging.
- Thixotropic, does not sag.

CONSUMPTION

Varies depending on the joint width.

PACKAGING

280 ml aluminum cartridges
600 ml aluminum sausages

APPLICATION

PREPARATION OF THE SURFACE

- The surface must be clear of materials which prevent bonding, such as dust, oil, tar, bitumen, paint, silicone, curing agents, detergents and mold release oils.
- The surface must be dry, non-humid.
- Clean non-porous surfaces such as aluminum, glass and metal with an appropriate solvent such as acetone, which does not cause any stain.
- Use **FIXA Polyethylene Backer Rod** in joints to reduce the consumption of PU 970.
- Mask the application area with masking tape for a smooth appearance and to prevent the material from contaminating the surrounding areas.
- Use **Polan A Polyurethane Floor Primer** for porous and absorbent surfaces.

APPLICATION

- PU 970 is ready-to-use.
- If PU 970 is in cartridge package, cut the tip of the cartridge is cut and place the nozzle which is cut with an appropriate angle to the tip of the cartridge. Open the aluminum cover under the cartridge. Apply without leaving any air.
- If PU 970 is in sausage type package, place it in an appropriate sausage gun and apply in joints without leaving any gap.
- Following the application, smooth the surface within 5 minutes, pressing with a spatula. This will enable PU 970 to adhere stronger and provide a better appearance of the filling.
- Consider the movement ability of the material when determining the joint width. The joint width must be between 5 mm minimum and 30 mm maximum.
- Remove the masking tape after the application. Clean the uncured sealant which is spread in undesired areas with a cleaning thinner. When curing is complete, it can only be cleaned mechanically.
- It can be overpainted, however take into account possible crack formations on the paint due to the joint movements.

CAUTION

- Avoid application below +5°C and above +35°C.
- Do not use in unventilated places since it needs the humidity in the air to be cured.
- The application area must definitely be non-humid.
- Do not use in environments where the chlorine amount is high.
- In cold weather, before the application, keeping PU 970 at +20°C for a while will make the application easier.
- Do not contact PU 970 with solvent, alcohol or cleaning materials which can damage its chemical structure before it is cured.

SHELF LIFE

Expires in 12 months. Store unopened packages in a dry, non-humid and cool environment, between +5°C and +30°C protected from sun light.



Technical Data Sheet (TDS)

Form No: 5.01 TDS PU 970
Rev: 05 – 02/2026

Date
09 June 2026

Page
3 / 3

HEALTH AND SAFETY

It contains isocyanate. As with all chemical products, contact with food, skin, eyes and mouth should be avoided during usage and storage. During the application, work wears, protective gloves and goggles should be used according to the work place health regulations. If swallowed by accident, consult a doctor. Swill in case of contact with skin. Long term and intensive inhaling of the solvent vapor which is released during the curing of the product can damage the respiratory system. The product should only be used in areas ventilated adequately. Avoid contact with uncured sealant for long time. Keep out of reach of children.

The application instructions and technical values given for the products have been obtained in accordance with our tests and experiences in accordance with international standards at $23\pm 2^{\circ}\text{C}$ temperature and $50\pm 5\%$ relative humidity conditions. These values may vary depending on ambient conditions. High temperatures shorten the times, low temperatures lengthen them. Before starting the application, the user should test whether the product is suitable for the application and purpose. FIXA Construction Chemicals Ltd. is not responsible. This Technical Data Sheet remains valid until the next revision is published. FIXA reserves the right to change the values specified in this Technical Data Sheet, provided that the new version is published. It is the user's responsibility to check that the document is up-to-date. Please contact our sales department for more information.