



Technical Data Sheet (TDS)

Form No: 5.01 TDS Repairfix 30
Rev: 04 – 01/2026

Date
10 July 2026

Page
1 / 2

Repair, Reinforcement and Restoration /
Cement Based Repair and Grout Mortars

REPAIRFIX® 30

Coarse Repair Mortar

APPLICATION

Cement based, single component, polymer and fiber added, **coarse aggregated** surface repair and smoothing mortar which offers a smooth finishing in concrete surfaces. Complies with **R2** class,

APPLICATION

- Indoor and outdoor,
- Horizontal and vertical applications,
- Restorations,
- Repairing concrete and prefabricated concrete elements,
- Smoothing and repairing wall and ceiling plaster,
- Prior to painting, ceramic covering and isolation in order to have a flat and sound surface. Suitable for **static cracks up to 30 mm**.

TECHNICAL PROPERTIES

Appearance	Grey colored coarse powder
Powder Density	~ 1.50 kg/L
Water Mixing Rate	4.5 – 5 L water / 25 kg powder
Resting Period	5 – 10 minutes
Pot Life	~ 30 minutes
Application Temperature	+ Between +5°C and +35°C
Bond Strength by Pull-off	≥ 0.8 N/mm ² (EN 1542)
Flexural Strength	≥ 5 N/mm ² (EN 196-1)
Compressive Strength	≥ 15 N/mm ² (EN 12190)
Service Temperature	Between -30°C and +80°C

ADVANTAGES

- Does not cause cracking and dusting.
- Only mixed with water and easy to apply.
- Dries quickly and allows utilization in a short period of time.
- Provides high adherence without primer.
- Resistant to water and freeze-thaw cycle.
- Fiber reinforced.

CONSUMPTION

2 kg/m² (for 1 mm thickness)

PACKAGING

25 kg kraft bags

APPLICATION

CONSUMPTION

- The surface must be cured.
- The surface must be clear of materials which prevent bonding, such as dust, oil, paint, curing agents, detergents, mold release oils and silicone.
- The surface must be wet and be kept damp

PREPARATION OF THE MORTAR

- Add 25 kg of REPAIRFIX 30 Coarse Repair Mortar to approximately 4.5 – 5 liters of clean water and mix with a low speed mixer or with a trowel, until there are no lumps.
- Leave the mortar to mature for 5 – 10 minutes, then is mix again 1 – 2 minutes before use.
- Use the mortar in 30 minutes.

APPLICATION

- Apply the repair mortar with a trowel to areas that have detached from the surface, cracked and broken.
- It can be applied between 5 – 30 mm thickness.
- It is recommended to keep the surface moist for 24 hours following the application.

CAUTION

- Avoid application below +5°C and above +35°C.
- Avoid application on frozen areas, on areas under risk of freezing in 24 hours or on areas open to direct sunlight or wind.
- Never add powder or water to the expired mortar.
- After the completion of the application, keep the surface damp until the mortar is cured.
- Do not apply on gypsum, ready colored plaster, paint and outer facade coatings.

SHELF LIFE

Expires in 12 months. Store unopened packages in non-humid environments. Stack up to 10 packages on the pallet.

HEALTH AND SAFETY

As with all chemical products, contact with food, skin, eyes and mouth should be avoided during usage and storing. During the application, work wears, protective gloves and goggles should be used according to the work place health regulations. If swallowed by accident, consult a doctor. Rinse with water in case of contact with skin. Keep out of reach of children.

The application instructions and technical values given for the products have been obtained in accordance with our tests and experiences in accordance with international standards at 23±2°C temperature and 50±5% relative humidity conditions. These values may vary depending on ambient conditions. High temperatures shorten the times, low temperatures lengthen them. Before starting the application, the user should test whether the product is suitable for the application and purpose. FIXA Construction Chemicals Ltd. is not responsible. This Technical Data Sheet remains valid until the next revision is published. FIXA reserves the right to change the values specified in this Technical Data Sheet, provided that the new version is published. It is the user's responsibility to check that the document is up-to-date. Please contact our sales department for more information.